BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images, please do not report the images to the Image Problem Mailbox.

B3

PCT WORLD INTELLECTUAL PROPI
International B

INTERNATIONAL APPLICATION PUBLISHED UNDER WO 9606196A1

(51) International Patent Classification 6 : C22C 18/04, H01M 4/42 — A1

(11) International Publication Number: WO 96/06196

(43) International Publication Date: 29 February 1996 (29.02.96)

(21) International Application Number: PCT/EP95/03229

(22) International Filing Date: 14 August 1995 (14.08.95)

(30) Priority Data:
9400758 23 August 1994 (23.08.94) BE

(71) Applicant *(for all designated States except US)*: N.V. UNION MINIERE S.A [BE/BE]; Gulledelle 92, B-1200 Brussels (BE).

(72) Inventors; and
(75) Inventors/Applicants *(for US only)*: STRAUVEN, Ivan, A., J. [BE/BE]; Hayenhoek 29, B-3580 Neerpelt (BE). MEEUS, Marcel, L. [BE/BE]; Zwaluwenlaan 12-1VC, B-8300 Knokke-Heist (BE).

(74) Agent: SAELEMAEKERS, Juul; N.V. Union Minière S.A., Gulledelle 92, B-1200 Brussels (BE).

(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, IS, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, TJ, TM, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).

Published
With international search report.

(54) Title: ZINC POWDER FOR ALKALINE BATTERIES

(57) Abstract

A zinc powder for alkaline batteries can comprise up to 20 ppm of iron if it further consists of 0.0005-1 % of aluminium, of a quantity of calcium such that the molar ratio aluminium/calcium amounts at most to 2 and such that the sum of the concentrations of aluminium and calcium amounts at most to 2 %, of 0.001-2 % of at least one of bismuth, indium and gallium, the rest being zinc.

ZINC POWDER FOR ALKALINE BATTERIES

This invention relates to an aluminium-containing zinc powder for alkaline batteries.

Aluminium-containing zinc powders are known from CA-A-2080762. The known powders comprise as impurity at most 1 ppm Fe and as alloying elements exclusively aluminium, bismuth and possibly either indium or lithium, or indium and calcium, or indium and lithium, as a result of which the evolution of gas is suppressed without having to make use of mercury and lead. The powders, however, have the disadvantage that their preparation requires special measures. Thus it is not possible to use cast zinc, and it is necessary to start from selected zinc cathodes which comprise ≤ 1 ppm Fe. The cathodes are fused together with the alloying elements and the smelt obtained is directly atomized. During these treatments, the atmosphere has to be conditioned so that it comprises less than 0.009 mg/m3 Fe. The powder obtained is subsequently further subjected to a magnetic separation in order to separate off the free iron. It is clear that those measures are somewhat cumbersome and costly. According to the applicant, even in those circumstances the risk remains high of contaminating the zinc powder with iron, for example through the materials used during the carrying out of the different treatments. Furthermore, most of the known powders exhibit the disadvantage that in a certain type of battery, namely the LR6 type, on discontinuous discharging they can give rise to short circuiting in the battery.

The object of the invention is to provide an aluminium-containing zinc powder for alkaline batteries that allows the disadvantages of the known powders to be avoided and that nevertheless has a satisfactory corrosion resistance.

The powder of the invention is characterized in that it consists of 0.0005-1 % of aluminium, of a quantity of calcium such that the molar ratio aluminium/calcium amounts at most to 2 and such that the sum of the concentrations of aluminium and calcium amounts at most to 2 %, of 0.001-2 % of at least one of bismuth, indium and gallium, the remainder being zinc, and in that it can comprise up to 20 ppm Fe.
By zinc is meant here and in the following thermally or electrolytically refined zinc (Special High Grade) and by percentages, percentages by weight.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria
AU	Australia
BB	Barbados
BE	Belgium
BF	Burkina Faso
BG	Bulgaria
BJ	Benin
BR	Brazil
BY	Belarus
CA	Canada
CF	Central African Republic
CG	Congo
CH	Switzerland
CI	Côte d'Ivoire
CM	Cameroon
CN	China
CS	Czechoslovakia
CZ	Czech Republic
DE	Germany
DK	Denmark
ES	Spain
FI	Finland
FR	France
GA	Gabon
GB	United Kingdom
GE	Georgia
GN	Guinea
GR	Greece
HU	Hungary
IE	Ireland
IT	Italy
JP	Japan
KE	Kenya
KG	Kyrgystan
KP	Democratic People's Republic of Korea
KR	Republic of Korea
KZ	Kazakhstan
LI	Liechtenstein
LK	Sri Lanka
LU	Luxembourg
LV	Latvia
MC	Monaco
MD	Republic of Moldova
MG	Madagascar
ML	Mali
MN	Mongolia
MR	Mauritania
MW	Malawi
NE	Niger
NL	Netherlands
NO	Norway
NZ	New Zealand
PL	Poland
PT	Portugal
RO	Romania
RU	Russian Federation
SD	Sudan
SE	Sweden
SI	Slovenia
SK	Slovakia
SN	Senegal
TD	Chad
TG	Togo
TJ	Tajikistan
TT	Trinidad and Tobago
UA	Ukraine
US	United States of America
UZ	Uzbekistan
VN	Viet Nam

The applicant forgoes, however, protection for the following compositions according to the invention:

- the compositions which comprise ≤ 1 ppm Fe and at the same time exclusively Al, Ca, Bi and In as alloying elements as those compositions are described in CA-A-2080762
- the compositions which comprise ≤ 1 ppm Fe and at the same time exclusively Al, Ca and Bi as alloying elements as those compositions are described in EP-A-0500313
- Zn - 0.01 % Al - 0.025 % Ca - 0.05 % In - 0.05 % Bi - 3 ppm Fe, as that composition is mentioned as a comparative example in CA-A-2080762
- Zn - 0.05 % Al - 0.05 % Ca - 0.05 % Bi - 3 ppm Fe, as that composition is mentioned as a comparative example in EP-A-0500313.

The applicant has found that zinc powder that simultaneously comprises aluminium and calcium such that the molar ratio Al/Ca ≤ 2 and such that the sum of the concentrations of Al and Ca is ≤ 2 %, gives rise to nearly no or no short circuiting in the battery in which it is used. At the same time, the applicant has found, as will be shown furthermore, that those powders can comprise up to 20 ppm Fe and still have a suitable corrosion resistance, more particularly after partial or complete discharging of the battery. The other alloying elements (Bi and/or In and/or Ga) give the powder a satisfactory corrosion resistance before discharging. The powder is thus also suitable for use in every type of battery such as LR6, LR14, LR20 and others.
The iron that the powder can comprise consists of the iron present as unavoidable impurity in the zinc and in the alloying elements and of the iron that is accidentally introduced into the powder during its preparation.

The molar ration Al/Ca amounts at most to 2, as at higher values short circuits can occur. The ratio is preferably at most 1.5, and especially at most 1.
The sum of the concentrations of Al and Ca amounts at most to 2%, preferably at most 1 % and especially at most 0.2 %. It is clear, when it is expected that the powder is going to have a fairly high Fe content, that the minimum quantity of Al and Ca that has to be added in order to obtain a suitable corrosion resistance will be higher than that quantity amounts to in the case of the powder having a low Fe content.

Further preferred compositions of the powder according to the invention form the object of the appended Claims 6-16.

A simple manner of producing the powder of the invention consists in adding all additives which should be present in the powder to be produced (for example Al, Ca and Bi) to molten zinc and to spray the alloy so obtained with gas, water or a mixture of both. It is also possible to spray molten zinc that already contains a portion of the additives (for example Al and Ca), after which the remainder of the additives (for example In) are deposited on the atomized powder, either by cementation from an aqueous solution, or by physical deposition from a gas phase ("Physical Vapour Deposition" or PVD), or by chemical deposition from a gas phase ("Chemical Vapour Deposition" or CVD). It is clear that the cementation technique can only be applied when dealing with additives which are more electropositive than zinc. When several additives are to be deposited on the atomized powder, these can be deposited simultaneously or separately.
It is also possible to introduce a particular additive partially via the molten zinc and the rest of it by deposition on to the atomized powder.
Instead of atomizing with gas, water or a mixture of both, any technique can be applied which is suitable for converting a molten metal to a powder, such as for example centrifugal atomization or casting and breaking up the cast metal.
If the desired powder contains additives capable of cementation (for example In), then yet another manner of preparing the powder of the invention consists in preparing a powder with the additives which are not capable of cementation, and possibly a portion of the additives which are capable of cementation, according to one of the methods described above and from the powder so obtained to make an anode which is fitted in the battery. The additives which are capable of cementation are added to the electrolyte of the battery, from where they cement on to the powder of the anode. Thus the powder according to the invention is obtained in the battery itself.
This invention thus not only relates to a powder which can be introduced into the battery, but also to a powder which is present in the battery.

The examples described in the following demonstrate that powders according to the invention do not cause short circuiting in the battery and have good resistance to corrosion in the electrolyte of the battery after partial discharge of the battery.

13 powders were made with the following composition:

(1) Zn - 70 ppm Al - 500 ppm Bi
(2) Zn - 70 ppm Al - 500 ppm Bi - 500 ppm In
(3) Zn - 70 ppm Al - 5000 ppm Bi - 500 ppm In

(4) Zn - 70 ppm Al - 500 ppm Bi - 500 ppm In - 150 ppm Ca
(5) Zn - 30 ppm Al - 500 ppm Bi - 500 ppm In - 110 ppm Ca
(6) Zn - 70 ppm Al - 500 ppm Bi - 500 ppm In - 40 ppm Ca
(7) Zn - 250 ppm Al - 500 ppm Bi - 500 ppm In - 110 ppm Ca
(8) Zn - 70 ppm Al - 150 ppm Ca - 500 ppm Bi
(9) Zn - 70 ppm Al - 180 ppm Ca - 500 ppm Bi - 500 ppm In
(10) Zn - 250 ppm Al - 250 ppm Ca - 500 ppm Bi - 500 ppm In
(11) Zn - 70 ppm Al - 180 ppm Ca - 250 ppm Bi - 250 ppm In
(12) Zn - 250 ppm Al - 250 ppm Ca - 500 ppm In
(13) Zn - 70 ppm Al - 150 ppm Ca - 500 ppm Bi - 100 ppm Ga

For this purpose the starting point is

- for powders (1)-(7), refined zinc selected for Fe content ≤ 1 ppm
- for powders (8)-(13), refined zinc that is commercially available

in fluid state to which the alloying elements are added in the desired quantities. The molten zinc solution thus obtained is homogenized at 450°C by stirring. The molten alloy is allowed to flow away in a stream of gas and in this way an alloy powder is produced, the particles of which have nearly the same homogeneous composition as that of the homogeneous molten solution. During these treatments for the alloys (1)-(7), the atmosphere is conditioned so that it contains less than 0.009 mg/m3 Fe. The alloys (8)-(13) are made in an unconditioned atmosphere.

The alloy powder is sieved so that the fraction which is larger than 500 mm and, in so far as this is possible, the fraction that is smaller than 104 mm is separated from it. In this way an alloy powder is obtained with a particle size distribution of 104 to 500 mm. The alloy powders (1)-(7) are subsequently further subjected to a magnetic separation in order to separate off the free iron. The Fe content of all these powders is determined, see the table below. The powders (1)-(7) are powders according to the previously mentioned prior art and the powders (8)-(13) are powders according to the invention.

With the alloy powder are then made

- batteries of the type LR14
- batteries of the type LR6 in which a commercial separator is used which has low density.

The LR14 batteries are discharged at 2.2 ohms for 6 h and then the quantity of hydrogen liberated is determined. The LR6 batteries are discharged discontinuously in order to check whether a

premature fall of the discharge curve occurs as a result of short circuiting. The results of both tests are presented summarized in the table below.

Powder No.	Fe ppm	mol Al/mol Ca	Gas µl/g/day	Short circuiting
(1)	≤ 1	-	110.3	yes
(2)	≤ 1	-	63.7	yes
(3)	≤ 1	-	220.9	yes
(4)	≤ 1	0.69	62.7	no
(5)	≤ 1	0.41	111.8	no
(6)	≤ 1	2.60	75.8	yes
(7)	≤ 1	3.38	60.9	yes
(8)	2	0.69	89.4	no
(9)	3	0.58	101.9	no
(10)	3	1.49	60.9	no
(11)	2	0.58	78.3	no
(12)	2	1.49	64.6	no
(13)	2	0.69	87.0	no

Comparison of examples nos. (1) - (7) with examples nos. (8) - (13) shows that the powders according to the invention have a good corrosion resistance and do not give rise to short circuiting in the battery.

Other typical examples of powders according to the invention have the following composition:

Zn - 50 ppm Al - 120 ppm Ca - 500 ppm In - 2 ppm Fe
Zn - 100 ppm Al - 120 ppm Ca - 500 ppm In - 2 ppm Fe
Zn - 100 ppm Al - 120 ppm Ca - 500 ppm Bi - 2 ppm Fe
Zn - 250 ppm Al - 500 ppm Ca - 500 ppm Bi - 3 ppm Fe
Zn - 500 ppm Al- 1000 ppm Ca - 500 ppm Bi - 3 ppm Fe
Zn - 250 ppm Al - 500 ppm Ca - 500 ppm Ga - 2 ppm Fe
Zn - 480 ppm Al - 1000 ppm Ca - 500 ppm Ga - 3 ppm Fe
Zn - 100 ppm Al - 150 ppm Ca - 250 ppm In - 250 ppm Bi - 2 ppm Fe

Zn - 500 ppm Al - 700 ppm Ca - 500 ppm In - 500 ppm Bi - 5 ppm Fe
Zn - 80 ppm A1 - 200 ppm Ca - 250 ppm In - 250 ppm Bi - 2 ppm Fe
Zn - 100 ppm Al - 180 ppm Ca - 250 ppm Ga - 250 ppm Bi - 2 ppm Fe
Zn - 120 ppm Al - 250 ppm Ca - 500 ppm Ga - 250 ppm Bi - 3 ppm Fe
Zn - 500 ppm Al - 1000 ppm Ca - 500 ppm Ga - 500 ppm Bi - 4 ppm Fe
Zn - 100 ppm Al - 200 ppm Ca - 250 ppm Ga - 250 ppm Bi - 250 ppm In - 2 ppm Fe
Zn - 700 ppm Al - 1200 ppm Ca - 500 ppm Ga - 500 ppm Bi - 250 ppm In - 3 ppm Fe
Zn - 1000 ppm Al - 1500 ppm Ca - 400 ppm Ga - 400 ppm Bi - 5 ppm Fe
Zn - 1000 ppm Al - 1200 ppm Ca - 250 ppm Ga - 400 ppm Bi - 3 ppm Fe
Zn - 250 ppm Al - 400 ppm Ca - 400 ppm Ga - 2 ppm Fe
Zn - 750 ppm Al - 1000 ppm Ca - 450 ppm Ga - 3 ppm Fe
Zn - 1000 ppm Al - 1000 ppm Ca - 300 ppm Ga - 2 ppm Fe
Zn - 350 ppm Al - 400 ppm Ca - 250 ppm Bi - 3 ppm Fe

These powders contain, besides zinc, Fe and the other unavoidable impurities, nothing other than the additives mentioned. The other unavoidable impurities are the impurities which are present in the zinc and in the additives.

CLAIMS

1. Aluminium-containing zinc powder for alkaline batteries, characterized in that it consists of 0.0005-1 % of aluminium, of a quantity of calcium such that the molar ratio aluminium/calcium amounts at most to 2 and such that the sum of the concentrations of aluminium and calcium amounts at most to 2 %, of 0.001-2 % of at least one of bismuth, indium and gallium, the remainder being zinc, and in that it comprises up to 20 ppm of iron; excluded being the aluminium-containing zinc powders comprising at most 1 ppm Fe and at the same time exclusively Al, Ca and either Bi, or Bi and In, the aluminium-containing zinc powder consisting of Zn, 0.01 % Al, 0.025 % Ca, 0.05 % In, 0.05 % Bi and 3 ppm Fe and the aluminium-containing zinc powder consisting of Zn, 0.05 % Al, 0.05 % Ca, 0.05 % Bi and 3 ppm Fe.

2. Powder according to Claim 1, characterized in that the molar ratio Al/Ca amounts at most to 1.5.

3. Powder according to Claim 2, characterized in that the molar ratio amounts at most to 1.

4. Powder according to Claim 1, 2 or 3, characterized in that the sum of the concentrations of Al and Ca amounts at most to 1 %.

5. Powder according to Claim 4, characterized in that the sum amounts to at most 0.2 %.

6. Powder according to one of Claims 1-5, characterized in that it comprises 10-1000 ppm Al.

7. Powder according to Claim 6, characterized in that it comprises 10-500 ppm Al.

8. Powder according to one of Claims 1-7, characterized in that it comprises 20-1000 ppm Bi.

9. Powder according to Claim 8, characterized in that it comprises 20-500 ppm Bi.

10. Powder according to one of Claims 1-9, characterized in that it comprises 20-1000 ppm In.

11. Powder according to Claim 10, characterized in that it comprises 20-500 ppm In.

12. Powder according to one of Claims 1-11, characterized in that it comprises 20-1000 ppm Ga.

13. Powder according to Claim 12, characterized in that it comprises 20-500 ppm Ga.

14. Powder according to one of Claims 1-13, characterized in that it comprises at most 10 ppm Fe.

15. Powder according to Claim 14, characterized in that it comprises at most 5 ppm Fe.

16. Powder according to Claim 15, characterized in that it comprises at most 3 ppm Fe.

17. Alkaline battery comprising an anode, a cathode and an electrolyte, characterized in that the anode comprises as active material a powder according to one of Claims 1-16.

18. Alkaline battery according to Claim 17, characterized in that the powder comprises metal cemented out of the electrolyte.

INTERNATIONAL SEARCH REPORT

Inte: xnal Application No
PCT/EP 95/03229

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C22C18/04 H01M4/42

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C22C H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 571 717 (MATSUSHITA ELECTRIC INDUSTRIAL CO.,LTD.) 1 December 1993 *Claims 1-3, 8-10, 13-15* ---	1-5
A	JP,A,4 289 661 (MITSUI MINING & SMELTING CO LTD) 14 October 1992 *Abstract* -----	1-7

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

1

Date of the actual completion of the international search	Date of mailing of the international search report
9 November 1995	21. 11. 95

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax (+31-70) 340-3016	Lippens, M

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

information on patent family members

Inte .nal Application No
PCT/EP 95/03229

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP-A-0571717	01-12-93	AU-B-	3372593	02-12-93
		US-A-	5384214	24-01-95
JP-A-4289661	14-10-92	NONE		